



tesa® 52994 PV 0



产品信息

永久防刮擦，防腐蚀和防石击

产品描述

tesa® 52994 由高透明的脂肪族聚氨酯薄膜和永久丙烯酸胶粘剂组成的复合物。

特点

- Highly transparent product design
- Resistant and durable against mechanical and environmental forces
- long-term UV resistance and self-healing properties without turning yellow over the vehicle's lifetime
- Good conformability makes it ideal for curves and complex surface geometries
- Dimension stability and die-cuttablity
- Compatible with several paint and clearcoat systems

应用

tesa® 52994 适用于永久保护表面抗腐蚀，抗冲击、重载、和防刮擦等机械损坏。该膜是专为外部使用而开发的，特别适用于喷漆表面。

技术参数 (平均值)

这里的数据仅应被视为参考值和典型值，不应被视为技术规范。

产品结构

- | | | | |
|---------|---------------|---------|--------|
| • 基材 | PU (聚氨酯) 薄膜 | • 总厚度 | 260 µm |
| • 胶粘剂类型 | 丙烯酸 | • 颜色 | 透明 |
| • 离型纸类型 | PET (聚酯) | • 离型纸颜色 | 半透明 |

产品系列

- | | | | |
|---------------------|--------------|-------------------------|--|
| • Available formats | 50m x 1245mm | • Available thicknesses | 187 µm (tesa® 52994 PV5), 260 µm (tesa® 52994 PV0), 360 µm (tesa® 52994 PV3) |
|---------------------|--------------|-------------------------|--|

属性/性能值

- | | | | |
|-----------|---------|---------------|-------|
| • 断裂延展率 | 340 % | • 耐化学品 | 好 |
| • 抗张强度 | 90 N/cm | • 耐高温性 | 是 |
| • 不光滑表面抛光 | 不 | • 耐温 (30分钟) | 90 °C |
| • 抗划伤性 | 普通 | • 耐磨 | 是 |
| • 服帖性 | 非常好 | • 适合模切 | 是 |

如需查询有关产品的最新信息，请访问 <http://l.tesa.com/?ip=52994>



tesa® 52994 PV 0

产品信息

储存条件

储存条件

If stored under proper conditions, product retains its performance and properties for 12 months from date of delivery.

附加信息

tesa® 52994可以根据客户的要求和应用提供再10毫米和200毫米宽度的卷料。

标准产品 (总厚度) :

tesa® 52994 PV0 - 260µm

tesa® 52994 PV3 - 360µm

免责声明

德莎产品定期经受严格的检验，在各种苛刻的条件下不断证明着自己卓然的优秀品质。我们在此提供的技术信息均来自我们基于实践经验获取的全部知识。这些技术参数应被看作平均值，而不可用于规范目的。因此，德莎不能做出任何明确或者隐含的担保——包含但不限于任何隐含的商品保证或适用于某特定目标的保证。因此，对于德莎产品是否适于某特定用途及适用于使用者的应用方法，使用者需要为自己的决定负责。如果您有任何疑问，我们专业的技术支持人员将非常乐意为您提供专业的咨询。



如需查询有关产品的最新信息，请访问 <http://l.tesa.com/?ip=52994>